

material characteristics	material number / grade	SWG 2083 VICTORY ESR			
	DIN standard	X40Cr14			
	comparable grade	1.2083mod ESR			
	chemical composition - reference analysis [%]	C	Si	Mn	Cr
		0.40	0.40	0.70	13.00
	production technology	EF/LF/VD/ESR, forging, Q+T (annealing)			
	service hardness / strength <small>converted acc. to DIN EN ISO 18265 table B2</small>		HB	HRC	N/mm ²
			308 - 568	32 - 54	-
	delivery condition	Q+T	308 - 341	32 - 36	980 - 1085
		annealed	≤ 250	-	-
maximum dimension	diameter		thickness		
	≤ 700 mm		≤ 500 mm		
US-specification	EN 10228-3		SEP 1921		
	table 3 - type 1 - qual. class 4		group 3 - class E,e		
cleanliness	DIN 50602		ASTM E45 method A		
	K1 ≤ 10		A ≤ 0,5; B, C, D ≤ 1		

variation upon request

technological properties		0	1	2	3	4	5	comment	
	toughness		■	■					in relation to service hardness 48 - 52 HRC
	hot strength at working temp.		■	■	■				
	wear resistance		■	■	■	■			
	corrosion resistance		■	■	■	■			polished surface for best corrosion resistance
	machinability		■	■	■				annealed
	polishability		■	■	■	■	■		ISO/SPI: N0/A-1
	weldability		■						CET = 1.12 % acc. DIN EN 1011-2
	texturability		■	■	■	■			
	nitridability		■	■	■	■			nitriding hardness 900 - 1200 HV1
chrome-platability		■	■	■	■			high cleanliness	

rating properties: 0 = not suitable; 1 = low; 2 = middle; 3 = good; 4 = very good; 5 = perfectly suitable

physical properties	thermal conductivity [W · m ⁻¹ · K ⁻¹]	20 °C	200 °C	300 °C	500 °C
		20.0	23.0	24.0	25.0
	coefficient of thermal expansion between 20 °C and ... [10 ⁻⁶ · K ⁻¹]	100 °C	200 °C	300 °C	500 °C
		10.5	11.0	11.0	11.6
elastic modulus [kN/mm ²]	20 °C	200 °C	300 °C	500 °C	
	218	206	198	180	


application	technology	mold making, injection molding, corrosion resistant
	tools	plastic molds, corrosion resistant, high surface quality
	process temperature	< 300 °C
	tool size	small- and medium-sized molds
	final products	plastic injection parts, high gloss, transparent
	features	pre-hardened up to 36 HRC delivery hardness

SWG processing instructions	welding, texturing, polishing, vacuum hardening
-----------------------------	--


heat treatment		T min [°C]	T max [°C]	medium / comment
	annealing	760	800	furnace
	hardening	1000	1030	vacuum, oil
	tempering	250	600	furnace, air
	stress relieving	450	500	max. 30 °C below tempering temp.
	pre-heating before welding	320	350	
	nitriding	400	500	max. 30 °C below tempering temp.
	PVD-treating	400	500	

diagrams/ structure	TTT-diagram	yes
	tempering diagram	yes
	advice on heat treatment	pre-hardened, annealing before new-hardening
	microstructure	martensitic

Tempering diagram: Average values on samples dia 25 mm x length 50 mm; hardened at 1020 °C in oil



TTT-diagram (continuous)



PLEASE NOTE: The information contained in this data sheet is unbinding. It merely serves the first orientation of the user. Therefore, we do not assume any liability for the correctness, completeness or up-to-dateness of such data. In case of an order, the properties of the product are exclusively subject to the provisions of the respective contract.

© Schmiedewerke Gröditz GmbH, Gröditz